



Color It! - Dye for Doll Hair

Please read directions carefully before starting

This is a professional dye for Mohair, Nylon, Silk or Wool doll hair. Everything you need is in the package. Always do test samples before working on a large project. For additional information, visit our web site at www.prochemicalanddye.com.

- ✘ Wear rubber gloves, apron or old clothes.
- ✘ All utensils used for dyeing should not be used for food preparation.

Immersion Dyeing for One Ounce (30 gm) of Doll Hair:

- 1. Wet out the fiber** in one gallon of warm (120°F/49°C) water bath containing ½ teaspoon (2.5ml) of Synthrapol.
- 2. For the dye pot**, use a stainless steel or unchipped enamel pan. Add 2 ½ cups (625ml) of room temperature 75°F to 95°F (24° to 35°C) water.
- 3. Measure ½ teaspoon** (1.25 gm) of the dye powder and dissolve the dye with a small quantity of boiling water. Add more water to equal one cup (250 ml). Mix well and add to your dyebath.
- 4. Squeeze out the excess water** from your doll hair and add to the dye bath.
- 5. Heat slowly to a boil (212°F/100°C)** while gently stirring, every now and then. If you are dyeing silk, raise the temperature no higher than 185°F/85°C, or you may lose the luster of the silk.
- 6. Keep the dyebath at a slow simmer** and dye the doll hair for 30 minutes, gently stirring every 5 or 10 minutes. Remove the pan from the heat and let the dyebath cool to room temperature.
- 7. Remove the doll hair and rinse** in warm (120°F/40°C) water, squeezing out excess water and letting the doll hair air dry.

© Copyright 2003